

XM TEXTILES
ROOM 2201, NO.18, SHUNYI ROAD, PUTUO DISTRICT

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : Woven fabric: Oxford-215 100%poly 215gsm Plain 600D*600D PU In Green

Proposed Care Instruction : 


Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Aug 20, 2012

Testing Period : Aug 20, 2012 TO Aug 23, 2012

Test Result(s) : For further details, please refer to the following page(s).

Signed for and on behalf of
SGS-CSTC Ltd.



Tina Xi
Account Executive

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) can be retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

Test Result

Dimensional Stability To Washing

(ISO 5077:2007/ISO 3759:2011/ISO 6330:2000/Amd 1:2008:Washing program No. 5A; Using front load, horizontal drum type machine wash at 40°C with 2kg total dry mass(knitted polyester ballast+ specimen)and 77% 'ECE' (A) + 3% TAED + 20% sodium perborate ,tumble dry low)

After 1 Wash

Lengthwise(%)	-0.4
Widthwise(%)	-0.4

Remarks: (+) Means extension (-) Means shrinkage

Colour Fastness To Washing

(ISO 105 C06:2010; Single test A2S, Machine wash at 40°C with 4g/l 'ECE(B)' detergent and 1g/l Sodium perborate solution with 10 steel balls.)

Change in shade	4-5
Staining on multi-fiber stripe	
Acetate	4-5
Cotton	4-5
Nylon	4
Polyester	4-5
Acrylic	4-5
Wool	4-5

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good

Colour Fastness To Rubbing

(ISO 105 X12:2001/Cor 2002; Size of rubbing finger: 16mm diameter.)

Dry staining	4-5
Wet staining	4-5

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good

Colour Fastness To Light

(ISO 105 B02:1994/Amd 1:1998+Amd 2:2000; use Xenon arc lamp)

Comparison upto blue wool reference 4

Grade (Bluewool Std)	4
----------------------	---

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

Tensile Strength

(ISO 13934-1:1999; CRE-50mm strip)

Warp/Length(N)	1500
Weft/Width(N)	1400

Tearing Strength

(ISO 13937-2:2000; Tongue Tear)

Warp yarns torn (N)	68
Weft yarns torn (N)	80

Hydrostatic Head Test

(ISO 811:1981 Hydrostatic Head; Rate of increase of water pressure :60 cm H₂O/min, temp of distilled water : 20°C,face side facing water)

As received

Water column (mm H₂O)

Individual reading :	
1#.	1043
2#.	1017
3#.	1032
4#.	1058
5#.	1012
Average :	1032

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) can be retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com