

Test Report No.: 0154136049a 001

Page 1 of 5

Client: SHANGHAI XM GROUP LTD


Office 2403~2403, 24th Floor, Zhongyi International Commercial Plaza, 1833
Zhongshan North Road, Shanghai, China

Contact Person: Anna He

Sample Description As Declared :

No. Of Sample : One(1)
Sample Description : Builder-240 100% cotton twill 3/1 240 GSM, Order-XNB-36/15, dark grey#8

**Applicant's Provided
Care Instruction/Label:**



Sample Receiving date: 2015-11-30

Delivery condition: Apparent good, Samples tested as received

Test Period: 2015-11-30 to 2015-12-04

**For and on behalf of
TÜV Rheinland (Shanghai) Co., Ltd.**



2015-12-04

Tina Wu / Department Manager

Date

Name/Position

Test result is drawn according to the kind and extent of tests performed.

This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

Conclusion

| | <u>M001</u> |
|----------------------------------|-------------|
| Tensile Strength | # |
| Tearing Strength | # |
| Dimensional Stability To Washing | # |
| Abrasion Resistance | # |
| Pilling Resistance | # |
| Colour Fastness To Washing | # |
| Colour Fastness To Perspiration | # |
| Colour Fastness To Rubbing | # |
| Colour Fastness To Light | # |

Note : P = Pass
= No Comment
N/A = Not Applicable

F = Fail
- = Did Not Perform
* = See Remark

Material list

| Material No. | Material | Color | Location |
|--------------|----------|--------------|--------------|
| M001 | Textile | Dark Grey #8 | Woven fabric |

1. Tensile Strength – Strip Test

Test method : ISO 13934-1:2013

M001

Breaking force

Warp 1400N

Weft 800N

2. Tearing Strength – Wing Rip Tear

Test method : ISO 13937-3:2000

M001

Warp 27N

Weft 27N

3. Dimensional Change To Washing

Test method : ISO 3759:2011 / ISO 6330:2012 / ISO 5077:2007

Apparatus : Front-loading horizontal rotating drum type

Test condition : Washing programme 6N, at 60°C, with 20g Non-phosphate detergent 3, 2kg loading (Type I), tumble dry - delicate

M001

After one wash

Warp -1.7%

Weft -3.0%

Remark: (+) = Extension

(-) = Shrinkage

4. Abrasion Resistance – Determination Of Specimen Breakdown

Test method : ISO 12947-2:1998+Cor.1:2002

M001

No. of rubs to breakdown >20000

Remark: Up to 20000Rubs

5. Pilling Resistance – Modified Martindale Method

Test method : ISO 12945-2:2000

No. of rubs : 2000

M001

Rating 3-4

6. Colour Fastness To Washing

Test method : ISO 105-C06:2010
 Test condition : C2S, 30 min mechanical wash at 60°C in 0.4% ECE reference detergent with phosphates and 0.1% sodium perborate with 25 steel balls

| | <u>M001</u> |
|-----------------|-------------|
| Colour change | 4-5 |
| Colour staining | |
| - Cotton | 4-5 |
| - Polyester | 4-5 |

7. Colour Fastness To Perspiration

Test method : ISO 105-E04:2013

| | <u>M001</u> | |
|-----------------|-------------|-----------------|
| | <u>Acid</u> | <u>Alkaline</u> |
| Colour change | 4-5 | 4-5 |
| Colour staining | | |
| - Acetate | 4-5 | 4-5 |
| - Cotton | 4-5 | 4-5 |
| - Polyamide | 4 | 4-5 |
| - Polyester | 4-5 | 4-5 |
| - Acrylic | 4-5 | 4-5 |
| - Wool | 4-5 | 4-5 |

8. Colour Fastness To Rubbing

Test method : ISO 105-X12:2001

| | <u>M001</u> |
|------------|-------------|
| <u>Dry</u> | |
| - Length | 4-5 |
| - Width | 4-5 |
| <u>Wet</u> | |
| - Length | 4 |
| - Width | 4 |

9. Colour Fastness To Light

Test method : ISO 105-B02:2013, Method 2
 Apparatus : Xenon-arc lamp

| <u>Up to Grade 4</u> | <u>M001</u> |
|----------------------|-------------|
| Grade | 3-4 |

Test Report No.: 0154136049a 001

Page 5 of 5

Sample Photo:



- END -